



PRODUCT DATA SHEET

77SF Silt Fence

PROPERTY	TEST METHOD	MARV
Tensile Strength (Grab)	ASTM D-4632	116/105
Elongation	ASTM D-4632	15%
Puncture	ASTM D-4833	60 lbs
Mullen Burst	ASTM D-3786	175 psi
Trapezoidal Tear	ASTM D-4533	58 lbs
UV Resistance	ASTM D-4355	70% AFTER 500 HRS
Apparent Opening Size (AOS)	ASTM D-4751	30 US Std. Sieve
Permittivity	ASTM D-4491	.05 sec ⁻¹
Water Flow Rate	ASTM D-4491	12 gpm/ft ²

The property values listed above are subject to change without notice.

Willacoochee Industrial Fabrics
Quality at Competitive Prices.

769 West Main Street
PO Box 599
Willacoochee, GA 31650

PH: 912-534-5757
FAX: 912-534-5533
www.winfabusa.com